

Resene product labels are updated from time to time. This label is provided as a guide for this product and may differ from the label on the container you purchase.
Please discuss your project with your local Resene ColorShop team or reseller to ensure you have the right products to give you the best quality finish for your specific project.

net contents 1 litre

LL1379201 2/20

SAFETY PRECAUTIONS

Keep out of reach of children. Read label before use. This material is quite bland; with vapour, occasional skin contact and even minor ingestion having negligible hazard. Repeated skin contact may, and any eye contact will, cause irritation.

PRECAUTIONS

USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well-ventilated area indoors, away from foodstuffs, at an ambient temperature and avoid freezing conditions. Avoid release to the environment.

FIRST AID

IF SWALLOWED: Rinse mouth. Call a POISON CENTRE, doctor or physician if you feel unwell.

IF ON SKIN (or hair): Rinse skin with plenty of soap and water. If skin irritation or rash occurs get medical attention or advice.

IF IN EYES: Rinse cautiously with water for several minutes. If eye irritation persists get medical attention or advice.

IF INHALED: If breathing is difficult, remove to fresh air and keep at rest in a position comfortable for breathing. If medical advice is required have product container or label at hand.

Further information can be obtained from
AUST: POISONS INFORMATION CENTRE 131 126
or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766)
or call Resene 0800 737 363.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet D324.

SPILLS: Wear appropriate clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Brush/roll out as much paint as possible onto newspaper before washing brushes and rollers. Dispose of wash-up water onto grassy/unsealed area or into inside sink/basin, NOT into outside stormwater drain where it may harm fish in local waterways.

Resene

FX Faux Rust Effect

exterior/interior



BASECOAT

Resene FX Faux Rust Effect is a waterborne coating system used to impart a rust style effect to a range of exterior and interior surfaces. Once applied, it provides you with the aesthetic effect of rusting that, like normal rust, will continue to develop as the coating ages.

Surface preparation

- Surfaces must be prepared and primed with the appropriate substrate primer prior to application of the Resene FX Faux Rust Effect basecoat.
- Ensure substrates to be coated are in sound condition, dry, free from dirt, dust, loose material, oil (including mineral oil based wood finishes or similar) and salt.
- Remove accumulated windblown salt by washing with Resene Paint Prep and Housewash (see Data Sheet D812).
- **All sanding dusts may be harmful and appropriate protection must be worn. In particular dusts from old lead or chromate based paints or old building materials containing asbestos may be injurious to health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.**
- This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, try a small test area first or contact your local Resene ColorShop or reseller for advice.

Priming

- Blockwork new: Two coats of Resene X-200 (see Data Sheet D62).
- Concrete/fibre cement old: Resene Sureseal (see Data Sheet D42).
- Concrete/fibre cement new: Resene Concrete Primer (see Data Sheet D405).
- GRC: Resene ConcreteSeal 3 in 1 (see Data Sheet D409).
- Timber (excludes Cedar/Redwood): Resene Quick Dry waterborne primer undercoat (see Data Sheet D45).
- Timber (Cedar/Redwood): Resene Wood Primer (see Data Sheet D40).
- Solid plaster: Resene LimeLock (see Data Sheet D809).

Application

- Work on a sample area first. This is especially important as the end result is dependent not only on the products but also on the style of application technique. Always agree on a sample panel with the applicator prior to the full project being undertaken. The sample size should be at least 70cm x 70cm (half a square metre).
- Apply two coats of Resene FX Faux Rust Effect basecoat using a wide brush, allowing at least 4 hours dry between coats. The final rust patterns will vary with application method and technique. Best effects are obtained with random direction brushstrokes. It is important to use a consistent technique. **DO NOT CUT IN AS THIS WILL RESULT IN PICTURE FRAMING.**
- Two coats of Resene FX Faux Rust Effect Activator give the best results. The deepest rust effect is obtained if the first application is applied as soon as the Resene FX Faux Rust Effect basecoat is tacky

or touch dry and should be completed within 24 hours of applying the Resene FX Faux Rust Effect basecoat. Apply the second application of activator as soon as the first is dry which is typically less than one hour. Apply the Resene FX Faux Rust Effect Activator solution by brush using random direction brushstrokes to completely cover the basecoat. Do not spray. Misted areas will not develop the rust effect.

- Rusting begins immediately after the activator is applied. Within one hour visual rust is noticeable and the majority of rust development occurs within 12 hours. A mist/brush/roll application of clean water 12-24 hours after application of the activator solution will produce a deeper rust effect. Repetitive water misting will increase the rate of rust development and the deeper the rust effect colour will be.
- High temperatures and low humidity will reduce the available working time. If necessary, add Resene Hot Weather Additive to the Resene FX Faux Rust Effect basecoat to slow drying.
- The Resene FX Faux Rust Effect Activator is corrosive. When applying close to any adjacent metal surfaces ensure plastic covers are in place to protect the metal surfaces against contact with the Resene FX Faux Rust Activator.
- The final colour may be protected (not sealed) by applying two coats of Resene Aquapel waterborne (see Data Sheet D65) diluted 2:1 with water. This provides a highly hydrophobic surface with water beading being maintained for 12 months. A slight deepening of the rust colour will result.

Be PaintWise

For tips on responsible disposal of paint, cleaning equipment and minimising the impact of your decorating on the environment see the Resene website. Do not discharge any paint into the environment. Resene PaintWise (NZ) or paintback.com.au (Australia) accepts residual unwanted paint and packaging. Or contact your Local Authority for disposal information.



FX Faux Rust Effect
SDS



FX Faux Rust Effect
TDS

Resene

the paint the professionals use

In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 924, Beenleigh, Qld 4207
Ph 1800 738 383 Visit www.resene.com.au

In New Zealand: Resene Paints Limited
Vogel St, PO Box 38242, Wgtn Mail Centre, Lower Hutt 5045
Ph (04) 577 0500 Visit www.resene.co.nz

Manufactured under a quality system certified as complying with ISO9001 by Telarc SAI, an accredited certification body. Printed on environmentally responsible paper which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

Quick check

Use on: Blockwork, concrete, fibre cement, G.R.C. panels, primed timber and solid plaster where a rust style effect is desired. Avoid use on contact areas as the finish may cause marking if brushed against. Not designed for direct to metal applications. DO NOT use in wet areas, such as bathrooms.

Finish: Flat.

Colour: Grey. Changes to orange/red rust effect finish after treatment with Resene FX Faux Rust Effect Activator. Will continue to rust after application.

The colour intensity and variation of Resene FX Faux Rust Effect will vary with application technique and to this end it is considered to be an artisan effect.

Theoretical coverage: Basecoat: 6-8 square metres per litre per coat dependent on surface and technique. Activator: 25 square metres per litre per coat dependent on surface and technique.

Dry time (minimum): 1 hour. Do not apply at temperatures below 10°C or when temperatures are liable to drop below this during the drying period. Drying is slowed by low temperatures and high humidity. Do not apply under damp conditions.

Recoat time (minimum): 4 hours.

Primer required: Yes.

Usual number of coats: Two, dependent upon on surface and finish. Consult your local Resene ColorShop or reseller.

Application method: Brush, natural sponge, clean rag. Small amounts of rust coloured run off can occur, even with the protected surface, for approximately one month (weather dependent) while unbound rust is washed from the surface. Apply Activator by brush - do not spray.

Thinning and clean up: Water. May be thinned with up to 5% clean tap water.

Hot conditions: In hot conditions may be thinned with up to 10% Resene Hot Weather Additive to slow drying. This is also useful when using Resene FX Faux Rust Effects on a large area.

Before use: Stir well with a wide flat stirrer.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy.

In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. Resene products are designed to be used as a system for optimal results. Substitution may cause substandard results or system failure. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.