Resene product labels are updated from time to time. This label is provided as a guide for this product and may differ from the label on the container you purchase. Please discuss your project with your local Resene ColorShop team or reseller to ensure you have the right products to give you the best guality finish for your specific project.

WARNING KEEP OUT OF REACH OF CHILDREN

Hesene

Qristal ClearFloor 2K waterborne flooring urethane

interior base



net contents 910ml LL2480001F 4/ **Open to read instructions.**

net contents 910ml

Must be mixed with the appropriate hardener. Makes 1 litre when mixed with 90 mL of Resene Oristal ClearFloor Satin hardener

SAFETY PRECAUTIONS

closed, in a well-ventilated area indoors, away from Read label before use. Keep out of reach of children foodstuffs, at an ambient temperature and avoid May cause an allergic skin reaction. freezing conditions. Wear protective gloves and clothing, eye and face protection. Contaminated work PRECAUTIONS clothing should not be allowed out of the workplace. DO NOT BREATHE MIST VAPOURS OR SPRAY

Store in original or correctly labelled container, tightly

FIRST AID

IF SWALLOWED: Call a POISON CENTRE, doctor or first aider if you feel unwell. IF INHALED: If breathing is difficult, remove to fresh air and keep at rest in a position comfortable for breathing If experiencing respiratory symptoms call a POISO CENTRE, doctor or first aider. IF ON SKIN (or hair): Wash with plenty of water. If ski irritation or rash occurs get medical advice or attentio Take off contaminated clothing and wash before reuse IF IN EYES: Rinse cautiously with water for seven minutes. Remove contact lenses if present and east to do so. Continue rinsing. If eve irritation persists ge medical advice or attention. If exposed or concerned get medical advice or attentio If medical attention is required have container or lab and SDS (Safety Data Sheet) at hand Further information can be obtained from AUST: POISONS INFORMATION CENTRE 131 126 or c Resene 1800 738 383

766) or call Resene 0800 737 363. CONTAINS: Adipic Dihydrazide 10-55 g/L For use as a decorative/protective coating. For full technical instructions see Data Sheet D506A SPILLS: Eliminate all sources of ignition and use

approved protective equipment. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or run off into water ways. Refer to local waste management authority.

CLEANING PAINT EOUIPMENT: Remove paint from roller sleeve using a roller scraper and then brush/rol out as much paint as possible onto newspaper befor washing out brushes or rollers with recommended clear up thinner. Do not allow washing residues to enter drains

or run off into water ways. Refer to your local Council for disposal of dirty solventborne thinners. FIRE: Blanket flames with dry chemical, carbon dioxide

or foam. Closed containers can explode when exposed NZ: NATIONAL POISONS CENTRE 0800 POISON (764 to extreme heat

Resene Oristal ClearFloor 2K is a two pack waterborne urethane durable flooring finish designed to protect your wooden flooring and keep it looking its best for longer. General

Read appropriate labels before use Users of this product should familiarise themselves with the Code of Practice for the Safe Use of Isocvanates issued by OSH. Read the Safety Data Sheet (SDS) and produ data sheet before use

 Stop all nail holes and cracked timber with a suitable filler. This product comprises a Base and Hardene Thoroughly sand surfaces prior to coating. Finish off with fine sandpaper. which must be mixed in the required ratio using remembering to sand with the grain. a power mixer before application. Add the total contents of the Hardener container to the tota contents of the base container. Once uniformly mixed allow to stand for the recommended applied to a floor that has areas of bare timber and old varnish. induction time prior to use.

 Mixed product does not require thinning; thinning is detrimental to product performance.

Drying is affected by low temperatures and high

 Use the mixed product within the stated pot li The pot life of the mixed material is given for a specific temperature. Higher temperatures will reduce the pot life: conversely lower temperatures will increase Mixed product will remain liquid well past stated pot life. Application of mixed product beyond stated pot life will have a detrimental effect upon film formation adhesion and performance.

 Substrate temperature should be 3°C above the "Dew Point" The "Dew Point" requirement can be presumed to be satisfied, if a thin clearly defined film of water applied to the cleaned surface with a damp cloth evaporates within 15 minutes

Ensure surfaces to be coated are in a sound condition, free from dirt, dust, loose

sanding dusts. Pay special attention to sanding dusts and residual floor polish in

All sanding dusts may be harmful and appropriate protection must be

worn. In particular sanding dusts from old lead or chromate-based paints

or old asbestos containing building materials may be injurious to health if

inhaled or ingested. Seek expert advice if the presence of these materials

WEAR PROTECTIVE GLOVES/CLOTHING AND EYE/FACE PROTECTION DURING

Gently shake the contents of the Base container and pour into a clean dry

Preparation

is suspected.

MIXING AND APPLICATION

Mixing

material, oil, grease and floor polishes.

the gaps between tongue and groove flooring.

• This product is designed for application to timber or timber composite this to the mixed base and power mix for a minimum of two minutes. flooring. If the surface you propose to coat is unsound or not referred to consult Allow mixed product to stand for 10-15 minutes before application. your nearest Resene Colorshop or reseller for your nearest Resene Technical Application Representative.

Apply by synthetic brush or Resene Waterborne Clears roller sleeve.

 Apply at the recommended spreading rate in an even manner to achieve uniform wet film thickness and lay-off with at least a 50% overlap. Do not

overwork the wet film to avoid increasing entrained air.

 Recoat when the applied coating is no longer milky in appearance and does no leave a fingerprint when pressed


container that will hold a minimum of six litres. Add the contents of the hardener

container to the base with power mixing. After mixing for one minute transfer some

of the mixed product back into the Hardener container, recap and shake to dissolve

any Hardener that was not originally transferred into the container of the Base. Add

 Lightly sand with 240 grit sandpaper prior to application of the final coat of clear. Drying is dependent upon temperature and humidity, poor ventilation may inhibit



Be PaintWise For tips on responsible disposal of paint, cleaning equipment and minimising

CAUTION

Do not tightly reseal quantities of leftover mixed product, as the mixed product generates carbon dioxide gas, which can cause the lid of a tightly sealed can to pop with force. Leave the mixed material in a safe place for at least 48 hours for outgassing to be completed before sealing cans for disposal through a Resene PaintWise location or approved hazard waste site.

not discharge any paint into the environment. Resene PaintWise (NZ) or paintback.com.au (Australia) accepts residual unwanted paint and packaging. Or contact your Local Authority for disposal information. Please recycle.

Resene

7 Production Ave. PO Box 918.

Ashmore City, OLD 4214

Ph 1800 738 383 Visit resene.com.au

In New Zealand: Resene Paints Limited

Vogel St, PO Box 38242, Wgtn Mail Centre,

Lower Hutt 5045

Ph (04) 577 0500 Visit resene.co.nz



Quick check

full cure

– 3 days at 18°C

Name: Resene Oristal ClearFloor 2K Generic type: Waterborne urethane acrylic. Pigmentation: None

Primer required: No. polication method: Synthetic brush or rol esene Waterhorne Clears sleeve) Not suitable

Thinning: Do not thin, supplied at application pplication to vertical surfaces. Clean up: Warm water and detergent. fixing ratio: 10 parts base: 1 part Satin Harde

Induction time: 10-15 minutes

Pot life: 4 hours at 18°C. DO NOT USE mixed produ eyond pot life, mixed product will remain in a liqui Recommended dry film thickness: 60-90 micro over sealed substrat

4 for heavy traffic areas.

cluding suitable breathing protection such as an Theoretical coverage: 10 square metres per litre air-supplied respirator or hood. at 30 microns

Usual number of coats: 3 for light Do not mix Resene Oristal ClearFloor 2K with Resene Colour Enhance.

Dry time (minimum): Tack free 1.5 hours at 18°C.

Drving is affected by low temperatures and high

Recoat time (minimum): 2 hours at 18°C Maximum

WHEN MIXED WITH THE CORRECT HARDENER

CONTAINS ISOCYANATES. When mixed with the

correct base and sprayed, this PRODUCT MAY BE

HARMFUL BY INHALATION. Do not breathe vapour or

spray. Avoid contact with skin and eyes. Wear suitable

protective clothing, gloves, eye and face protection

humidity. Allow seven days for coating to reach

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy

Read the appropriate Data Sheet and Safety Data Sheet before application.

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. Resene does not accept any responsibility for the <u>application</u> of incorrect product to substrate or the <u>application</u> of incorrect responsibility for the <u>application</u> of incorrect product to substrate or the <u>application</u> of incorrect colours. Resene products are designed to be used as a system for optimal results. Substitution may cause substandard results or system failure. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.

the impact of your decorating on the environment see the Resene website. Do

the paint the professionals use In Australia: Resene Paints (Aust) Limited

Qristal ClearFloor 2K Base SDS